# KRET SWIRL

Kret Clay · Swirl

## M20 PLASTERED, RENDERED AND ROUGHCAST COATINGS

### M20/145 KRET SWIRL

| | |
|---|---|
| Manufacturer | Kret Co., Ltd., Bangkok, Thailand · hello@kret.co.th |
| Product reference | Kret Clay · Swirl |
| Product type | Hand-applied texture made from Kret Clay |
| Base | Kret Clay |
| Substrate | Render, blockwork or board, primed |
| Primer | Kret Primer |
| System | 1–2 coats, 2–4 mm total |
| Build | 2–4 mm |
| Colour | Kret colour: [Code and name, for example MF-05 Yogurt White] |
| Finish | Matt, as approved sample |
| Protection | Breathable sealer in high-touch areas |
| Technical data | Kret technical data sheet KRET-TDS-009; safety data sheet KRET-SDS-009 |

### 210 SUPPLY AND APPLICATION

| | |
|---|---|
| Requirement | Supply and apply by Kret Co., Ltd. using its own trained crews. No other applicator to be used. |
| Submittals | Data sheets, colour reference and programme before work starts. |

### 220 SAMPLE PANEL

| | |
|---|---|
| Size | Not less than 1 m², on the project substrate, in the specified colour and finish. |
| Approval | Obtain approval of the panel in site lighting before starting work. The approved panel is the standard for the whole installation. Retain until completion. |

### 230 SUBSTRATE PREPARATION

| | |
|---|---|
| Requirement | Sound, dry, clean, free of dust, grease, efflorescence and loose material. |
| New render or blockwork | Cured for at least 28 days. |
| Flatness | Within 3 mm under a 2 m straightedge before application. |

### 240 ENVIRONMENTAL CONDITIONS

| | |
|---|---|
| Temperature | +8 °C to +35 °C |
| Relative humidity | Below 85% |
| Protection | Protect from rain, direct sun and strong wind until dry. |

### 250 APPLICATION

| | |
|---|---|
| Method | In accordance with the Kret technical data sheet and the approved sample panel. |
| Joints | No visible joints or laps except at architectural breaks, corners or agreed stop lines. |
| Adjacent surfaces | Mask and protect. Remove splashes immediately. |

### 260 COMPLETION

| | |
|---|---|
| Inspection | Inspect with the contract administrator in normal lighting. Make good defects to match the approved sample. |
| Handover | Remove masking, clean down and hand over the Kret care and maintenance guidance. |

**Using this clause.** Copy into the project specification and complete the bracketed items. Kret can supply an edited clause for your project on request: hello@kret.co.th