Kret Plaster · Coarse mineral

TEXTURE (LARGE)

A coarse, open mineral plaster with a deep texture that catches raking light.

Texture (Large) carries a coarse aggregate, so the surface is open and deep, with real relief that changes through the day as the light moves.



TEXTURE (LARGE) · KRET, BANGKOK

COVERAGE	DRY TO TOUCH	PACKAGING
5–7 kg/m² at 4–6 mm	4–6 hours	25 kg pail

AREAS OF USE

- Feature walls
- Entrances
- Covered exteriors

FEATURES

- Coarse, open texture
- Deep relief in raking light
- Interior and covered exterior
- Hides uneven substrates
- Hard-wearing mineral finish
- Low in VOCs

TECHNICAL DATA

PRODUCT TYPE	Lime-based coarse granular plaster, ready to use
COMPOSITION	Slaked lime, graded marble and quartz grain up to 2 mm, mineral pigments
COLOUR	Any of the 75 Kret colours, or matched to a sample
FINISH	Matt, coarse granular
BUILD	4–6 mm
TOOLS	Trowel, float or spray

AREAS OF USE	Feature walls, entrances, covered exteriors
SUBSTRATES	Render, blockwork or board, primed
PROTECTION	Breathable sealer
COVERAGE	5–7 kg/m² at 4–6 mm
COATS	1–2 coats, 4–6 mm total
DENSITY	1.8 ± 0.05 kg/L
PH	12–13
VOC CONTENT	< 1 g/L
REACTION TO FIRE	A1 (EN 13501–1)

APPLICATION CONDITIONS AND DRYING

MIXING	Do not thin.
WORKING TIME	Ready to use.
APPLICATION TEMPERATURE	+8 °C to +35 °C
RELATIVE HUMIDITY	Below 85%
DRY TO TOUCH	4–6 hours
RECOAT	24 hours
FULL CURE	28 days

Times given at 25 °C and 60% relative humidity. Lower temperatures and higher humidity lengthen them.

SURFACE PREPARATION

01 Substrate must be sound, dry, clean and free of dust, grease, efflorescence and loose paint.

02 Fill cracks and holes and allow repairs to cure. New render or blockwork: allow at least 28 days.

03 Plasterboard: tape and fill joints, then prime.

04 Apply Kret Primer by roller and allow to dry for at least 4 hours before the first coat.

APPLICATION

01 Stir to an even paste.

02 Apply by trowel or plaster spray to 4–6 mm.

03 Float or texture to the approved sample while the surface is still workable.

04 Covered exteriors: apply Kret Breathable Sealer once fully dry.

AFTERCARE

- Protect fresh work from rain, direct sun, strong wind and frost for at least 48 hours.
- Mist with clean water in hot or dry conditions to slow drying and help carbonation.

CLEANING AND MAINTENANCE

- Tools and spray equipment in clean water straight after use.
- Brush or wipe with a damp cloth.

PACKAGING AND STORAGE

PACKAGING	25 kg pail
SHELF LIFE	12 months in the unopened pail
STORAGE	Store sealed, upright, between +5 °C and +35 °C, out of direct sun. Do not freeze.

HEALTH AND SAFETY

- Contains lime or cement: alkaline. Causes serious eye damage and skin irritation.
- Wear gloves, eye protection and long sleeves. Wear a dust mask when mixing powders or sanding.
- Eyes: rinse at once with plenty of clean water for at least 15 minutes and seek medical advice.
- Keep out of reach of children. Do not empty into drains. See the safety data sheet.

Important. The values on this sheet are typical results from testing at 23 °C and 50% relative humidity. Site conditions, substrates and application affect the result, so final values are confirmed per project on the approved sample. Always trowel a sample panel on site before work begins. This issue supersedes all previous issues. **Kret Co., Ltd.** · Bangkok, Thailand · hello@kret.co.th