Kret Plaster · Fine mineral

TEXTURE (SMALL)

A fine, sandy mineral plaster. Soft texture you can see, and feel when you run a hand along the wall.

Texture (Small) is a mineral plaster carrying a fine aggregate, so the texture lives in the material rather than being drawn on afterwards. It reads as a soft, sandy skin that softens light without shouting.



TEXTURE (SMALL) · KRET, BANGKOK

COVERAGE	DRY TO TOUCH	PACKAGING
2.5–3.0 kg/m² for two coats	3–5 hours	25 kg pail

AREAS OF USE

- Walls
- Ceilings
- Vaults
- Curved surfaces

FEATURES

- Fine, sandy texture
- Texture built into the material
- Wraps curves, vaults and ceilings
- Hides minor substrate defects
- Breathable mineral finish
- Low in VOCs

TECHNICAL DATA

PRODUCT TYPE	Lime-based granular plaster, ready to use
COMPOSITION	Slaked lime, graded marble and quartz grain up to 0.6 mm, mineral pigments
COLOUR	Any of the 75 Kret colours, or matched to a sample
FINISH	Matt, fine granular
BUILD	About 2 mm
TOOLS	Trowel or float

AREAS OF USE	Walls, ceilings, vaults, curved surfaces
SUBSTRATES	Render, blockwork or board, primed
PROTECTION	Breathable sealer in high-touch areas
COVERAGE	2.5–3.0 kg/m² for two coats
COATS	2 coats, about 1 mm each
DENSITY	1.75 ± 0.05 kg/L
PH	12–13
VOC CONTENT	< 1 g/L
REACTION TO FIRE	A2–s1, d0 (EN 13501–1)

APPLICATION CONDITIONS AND DRYING

MIXING	Do not thin.
WORKING TIME	Ready to use.
APPLICATION TEMPERATURE	+8 °C to +35 °C
RELATIVE HUMIDITY	Below 85%
DRY TO TOUCH	3–5 hours
RECOAT	24 hours
FULL CURE	28 days

Times given at 25 °C and 60% relative humidity. Lower temperatures and higher humidity lengthen them.

SURFACE PREPARATION

01 Substrate must be sound, dry, clean and free of dust, grease, efflorescence and loose paint.

02 Fill cracks and holes and allow repairs to cure. New render or blockwork: allow at least 28 days.

03 Plasterboard: tape and fill joints, then prime.

04 Apply Kret Primer by roller and allow to dry for at least 4 hours before the first coat.

APPLICATION

01 Stir to an even paste.

02 Apply the first coat with a steel trowel to grain thickness.

03 Apply the second coat and float with a plastic float in small circles for an even grain.

04 On curves and vaults, work in small bays and keep a wet edge.

AFTERCARE

- Protect fresh work from rain, direct sun, strong wind and frost for at least 48 hours.
- Mist with clean water in hot or dry conditions to slow drying and help carbonation.

CLEANING AND MAINTENANCE

- Tools in clean water straight after use.
- Wipe with a damp cloth.

PACKAGING AND STORAGE

PACKAGING	25 kg pail
SHELF LIFE	12 months in the unopened pail
STORAGE	Store sealed, upright, between +5 °C and +35 °C, out of direct sun. Do not freeze.

HEALTH AND SAFETY

- Contains lime or cement: alkaline. Causes serious eye damage and skin irritation.
- Wear gloves, eye protection and long sleeves. Wear a dust mask when mixing powders or sanding.
- Eyes: rinse at once with plenty of clean water for at least 15 minutes and seek medical advice.
- Keep out of reach of children. Do not empty into drains. See the safety data sheet.

Important. The values on this sheet are typical results from testing at 23 °C and 50% relative humidity. Site conditions, substrates and application affect the result, so final values are confirmed per project on the approved sample. Always trowel a sample panel on site before work begins. This issue supersedes all previous issues. **Kret Co., Ltd.** · Bangkok, Thailand · hello@kret.co.th