Kret Texture (Large) · Splash

SPLASH

Texture (Large) thrown onto the wall by hand, then lightly pressed. A deep, rough surface that comes alive in raking light.

Splash is made from Texture (Large). The crew throws the plaster onto the wall in handfuls and presses it back lightly, so every wall carries its own pattern of peaks and hollows. It is the traditional roughcast technique, refined for interiors.



SPLASH · KRET, BANGKOK

COVERAGE	DRY TO TOUCH	PACKAGING
6–10 kg/m² at 4–8 mm	4–6 hours	25 kg pail

AREAS OF USE

- Feature walls
- Columns
- Entrances
- Covered exteriors

FEATURES

- Deep, rough, hand-thrown surface
- Every wall is unique
- Comes alive in raking light
- Interior and covered exterior
- Hides uneven substrates
- Made from Texture (Large)

TECHNICAL DATA

PRODUCT TYPE	Thrown texture made from Kret Texture (Large)
COMPOSITION	Slaked lime, graded marble and quartz grain to 2 mm, mineral pigments
COLOUR	Any of the 75 Kret colours, or matched to a sample
MADE FROM	Texture (Large)
BUILD	4–8 mm
APPLICATION	Thrown by hand, lightly pressed

AREAS OF USE	Feature walls, columns, entrances, covered exteriors
SUBSTRATES	Render, blockwork or board, primed
PROTECTION	Breathable sealer in high-touch areas
COVERAGE	6–10 kg/m² at 4–8 mm
COATS	1 base coat, 1 thrown coat
DENSITY	1.8 kg/L
PH	12–13
VOC CONTENT	< 1 g/L
REACTION TO FIRE	A1 (EN 13501-1)

APPLICATION CONDITIONS AND DRYING

MIXING	Do not thin.
WORKING TIME	Ready to use.
APPLICATION TEMPERATURE	+8 °C to +35 °C
RELATIVE HUMIDITY	Below 85%
DRY TO TOUCH	4–6 hours
RECOAT	24 hours
FULL CURE	28 days

Times given at 25 °C and 60% relative humidity. Lower temperatures and higher humidity lengthen them.

SURFACE PREPARATION

01 Substrate must be sound, dry, clean and free of dust, grease, efflorescence and loose paint.

02 Fill cracks and holes and allow repairs to cure. New render or blockwork: allow at least 28 days.

03 Plasterboard: tape and fill joints, then prime.

04 Apply Kret Primer by roller and allow to dry for at least 4 hours before the first coat.

APPLICATION

01 Apply a tight base coat and leave to firm up.

02 Throw the texture coat onto the wall by hand or with a hopper.

03 Press lightly with the trowel to flatten the peaks, matching the approved sample.

AFTERCARE

- Protect fresh work from rain, direct sun, strong wind and frost for at least 48 hours.
- Mist with clean water in hot or dry conditions to slow drying and help carbonation.

CLEANING AND MAINTENANCE

- Tools in clean water.
- Brush off dust.

PACKAGING AND STORAGE

PACKAGING	25 kg pail
SHELF LIFE	12 months in the unopened pail
STORAGE	Store sealed, upright, between +5 °C and +35 °C, out of direct sun. Do not freeze.

HEALTH AND SAFETY

- Contains lime or cement: alkaline. Causes serious eye damage and skin irritation.
- Wear gloves, eye protection and long sleeves. Wear a dust mask when mixing powders or sanding.
- Eyes: rinse at once with plenty of clean water for at least 15 minutes and seek medical advice.
- Keep out of reach of children. Do not empty into drains. See the safety data sheet.

Important. The values on this sheet are typical results from testing at 23 °C and 50% relative humidity. Site conditions, substrates and application affect the result, so final values are confirmed per project on the approved sample. Always trowel a sample panel on site before work begins. This issue supersedes all previous issues. **Kret Co., Ltd.** · Bangkok, Thailand · hello@kret.co.th